

## Dulux AcraTex 959 Mediterranean Classique Bagged Look

AUDA1444

Part A	194-85950
--------	-----------

### Product Overview

DULUX AcraTex Mediterranean Classique is an extremely tough 100% pure acrylic high build coating, especially formulated to produce a granular, near flat, appearance very much like that of a bagged finish render in a single or multi coat application.

### Features And Benefits

- |  |  |
|--|--|
| <ul style="list-style-type: none"> <li>• Water based</li> <li>• Versatile application</li> <li>• Leading acrylic polymer science</li> <li>• Low or high build profile</li> </ul> | <ul style="list-style-type: none"> <li>• Easy, safe and economical clen up</li> <li>• Elegant and variable decorative finish</li> <li>• Quick,efficient application with roller, brush and mitt</li> </ul> |
|--|--|

### Uses And Typical Specifications

<b>Uses</b>	DULUX AcraTex Mediterranean Bag Finish Classique is a flexible Full Acrylic, tintable, Texture Coating applied directly from the bucket in one or multiple coats by mitt applicator and finished in various ways by bagging mitt, texturing brushes or broom finish to the desired feature texture style. Typically applied over suitably prepared flush jointed brickwork softening the hard line brick profile with feature colour and texture. Specified in system with AcraShield weather-proofing barrier topcoat for optimum life cycle efficiency																													
<b>Typical Systems</b>	<p><b>Typical System</b> DULUX Acratex Mediterranean Classique on New Un-coated Block</p> <p><b>Preparation Guide</b> Refer Duspec for full Details</p> <table border="1"> <thead> <tr> <th>Coat</th> <th>Product</th> <th>Spread Rate (m<sup>2</sup>/L)</th> <th>WFT (micron)</th> <th>DFT (micron)</th> </tr> </thead> <tbody> <tr> <td>1st Coat</td> <td>Acraprime Water Based</td> <td>10</td> <td>60</td> <td>20</td> </tr> <tr> <td>2nd Coat</td> <td>959 Mediterranean Classique</td> <td>0.9</td> <td>1116</td> <td>500</td> </tr> <tr> <td>3rd Coat</td> <td>AcraShield Advance</td> <td>6.0</td> <td>167</td> <td>75</td> </tr> <tr> <td colspan="4"><b>Minimum System DFT</b></td> <td>595</td> </tr> </tbody> </table>					Coat	Product	Spread Rate (m <sup>2</sup> /L)	WFT (micron)	DFT (micron)	1st Coat	Acraprime Water Based	10	60	20	2nd Coat	959 Mediterranean Classique	0.9	1116	500	3rd Coat	AcraShield Advance	6.0	167	75	<b>Minimum System DFT</b>				595
Coat	Product	Spread Rate (m <sup>2</sup> /L)	WFT (micron)	DFT (micron)																										
1st Coat	Acraprime Water Based	10	60	20																										
2nd Coat	959 Mediterranean Classique	0.9	1116	500																										
3rd Coat	AcraShield Advance	6.0	167	75																										
<b>Minimum System DFT</b>				595																										

## Precautions And Limitations

To ensure colour uniformity and for optimum performance, Dulux recommend a full coating system including a MEMBRANE top coat. For ALL systems the Texture &/or Base Coat should be tinted in accordance with AcraTex Tint Guide to the specified top coat colour (or a colour as close as possible to the specified colour as product and tint rules allow). **IMPORTANT:** Not all colours are suitable for exterior use. This product data sheets is to be read in conjunction with DULUX specification. Ensure that you have adequate tinted stock to complete the job in one application. All material must be thoroughly cross-mix to ensure tint uniformity. It is recommended to hold a volume of finish material for future maintenance touch-ups

Practical spreading rates will vary from quoted theoretical figures depending on substrate porosity, surface roughness, overspray losses, application methods and environmental conditions (e.g. wind).

All preparation and painting must conform to AS2311: The Painting of Buildings

At Commencement of coating system application, to the substrate it shall be deemed that the Applicator has certified that the surface which the coating/s is to be applied to, is fit to receive the specified coating(s) system.

Do not apply paint if Relative Humidity is above 85% or temperature is within 3°C of Dew Point.

Do not apply if the surface temperature is greater than 40°C or below 10°C, or likely to fall below 10°C during the application or drying period.

Dry times apply to a single coat at recommended spread rate and at 25°C and 50% Relative Humidity

Allow longer times under cool, moist, or still conditions and or when applied at high film builds.

Protect from dew, rain and frost for 48 hours when apply at the recommended spread rate.

Avoid application in hot, windy conditions or on hot surfaces cool the surface by hosing with water and paint the cool damp surface.

Application techniques should be adjusted to achieve the recommended DFT and finishing standard.

To avoid "Picture Framing" of texture topcoats "wet on wet" cutting in & coating technique is recommended or apply multiple coats thinning the first coat.

When using Bright Reds, Oranges, Blues and Yellows or where very light (or dark) colours are applied over highly contrasting colours an extra coat maybe required.

The coastal area is considered a marine environment and as such salt potentially can shorten the life of the coating systems. Care needs to be taken to wash down all areas twice. Once to remove surface contaminants, and raise salts to the surface and then secondly to remove these salts. Due to the locality, weather conditions and lag time between applications of the coating system it may require the need to wash again, between coats.

When the Applicator is preparing the site sample for approval he should advise the Project Superintendent if the substrate condition is not of sufficient standard to produce the specified finish.

Where possible avoid dark colours - these will give raise to much higher surface temperature that may cause addition thermal stress and cooling demand to the building envelope and/ or require extra engineering considerations (greater building costs).

Consult Dulux on the potential to use InfraCOOL Heat Reflective Coatings.

A DULUX warranty can be provided on request, when the FULL AcraTex system including a membrane topcoat/s is applied by a DULUX AcraTex trained applicator, according to specification, & at the specified spreading rates, & to the surface preparation details described in the DULUX AcraTex Specification Manual.

The dynamics of the substrate is outside the control of Dulux Australia and as such joint deformation or cracking is excluded from warranty terms.

Colour change is a natural part of a coating weathering and is excluded from warranty terms

Refer warranty document for full terms and conditions.

CEMENT RENDERS PRODUCE FINE CRACKS DURING DRYING AND CONTINUE TO CRACK & MOVE WITH VARIATIONS IN TEMPERATURE.

FOR ENHANCED PERFORMANCE USE A HIGH BUILD ELASTOMERIC (FLEXIBLE) COATING.

DULUX RECOMMENDS THE USE OF DULUX ACRASHIELD ADVANCE.

Fungi and Algae can exist on virtually any surface (even glass) provided the right conditions for growth are met.

Visible growth on painted surfaces is typically caused by contaminants present together with the presence of high enough levels of moisture to support growth. Agents in paints become ineffective where they cannot "touch" the growth source (eg where growth emanates from deposits on the film).

Additionally the active agents are "consumed" in the process such that protection is time limited where conditions support ongoing growth performance is greatly improved with the inclusion of a membrane Top coat like Dulux AcraTex AcraShield Advance, Elastomeric 201 or AcraSkin.

Refer: <http://www.dulux.com.au/specifier/our-brands/dulux-acratex/more-than-just-render>

The exterior texture coatings should be cleaned on a regular basis. This will help maintain your overall aesthetic appearance and preserve your AcraTex Texture coating system. Cleaning once every year will remove light soil as well as grime and airborne pollutants refer Dulux AcraTex Care & Maintenance Guide. Refer <http://www.dulux.com.au/specifier/our-brands/dulux-acratex/acratex-care-and-maintenance>

### SURFACTANT LEACHING FROM EXTERIOR WATER-BASED COATINGS



Occasionally amber, clear or white spots/streaks are seen on a newly painted surface within the first few weeks after application. They usually appear after light rain or overnight dew and generally located in sheltered areas or areas with limited sun exposure. Under normal conditions surfactant contained in the tinted paint colour is slowly leached to the surface and washed away by rain leaving no trace and is a normal part of drying of any exterior water-based paint. Under certain atmospheric conditions and these surfactants leach or migrate to the paint surface, is concentrated forms and leaves clear or white deposits upon drying. These conditions include cool or humid weather or painting cold substrate and in most cases these marks on the wall surfaces are more noticeable on dark colours, such as browns or dark greens, etc..

The clear/white surfactants that have migrated to the wall surface areas will cause no down grading nor performance changes or long term durability concerns of the paint films integrity and unfortunately have become an appearance issue instead.

They easily removed from the paint film within a week or so of their appearance by washing with warm water & commercial grade detergent or via Nifti or Spray'nWipe followed by rinsing with fresh clean water.

Under severe conditions they may reappear once or twice until all the surfactant has been removed. It will be less noticeable each time, and can be removed in the same manner as before. Refer [http://www.dulux.com.au/pdf/tech-advice/DLX\\_TECH\\_Leaching.pdf](http://www.dulux.com.au/pdf/tech-advice/DLX_TECH_Leaching.pdf)

Performance Guide			
<b>Weather</b>	Excellent resistance to cracking, flaking and chalking as part of full system.	<b>Salt</b>	Resists salt spray especially when top coated with DULUX AcraTex AcraShield.
<b>Heat Resistance</b>	Up to 90C (dry).	<b>Water</b>	N/A
<b>Solvent</b>	Resists alcohol and aliphatic hydrocarbons. Sensitive to strong solvents.	<b>Abrasion</b>	Good abrasion resistance especially when top coated with DULUX AcraTex AcraShield.
<b>Acid</b>	N/A	<b>Alkali</b>	N/A

Typical Properties																											
<b>V.O.C Content</b>	57	<b>Clean Up</b>	Clean up water																								
<b>Application Method</b>	  Brush      Roller  <b>Other:</b> Mediterranean Classique can also be applied by Hawk and Trowel then Lambswool Mitt textured or br Lambswool Mitt direct to substrate. Note: Various finishing techniques combined with multiple coats can be applied to create different finishes.																										
<b>Application Conditions</b>	<table border="0"> <tr> <td><b>Solids By Volume</b></td> <td>44.81</td> <td></td> <td></td> </tr> <tr> <td></td> <td><b>Min</b></td> <td><b>Max</b></td> <td><b>Recommended</b></td> </tr> <tr> <td><b>Wet Film Per Coat (microns)</b></td> <td>893</td> <td>1451</td> <td>1116</td> </tr> <tr> <td><b>Dry Film Per Coat (microns)</b></td> <td>400</td> <td>650</td> <td>500</td> </tr> <tr> <td><b>Recoat Time (min)</b></td> <td>4 Hours</td> <td>Indefinite</td> <td></td> </tr> <tr> <td><b>Theoretical Spread Rate (m<sup>2</sup>/L)</b></td> <td>1.1</td> <td>0.7</td> <td>0.9</td> </tr> </table>	<b>Solids By Volume</b>	44.81				<b>Min</b>	<b>Max</b>	<b>Recommended</b>	<b>Wet Film Per Coat (microns)</b>	893	1451	1116	<b>Dry Film Per Coat (microns)</b>	400	650	500	<b>Recoat Time (min)</b>	4 Hours	Indefinite		<b>Theoretical Spread Rate (m<sup>2</sup>/L)</b>	1.1	0.7	0.9		
<b>Solids By Volume</b>	44.81																										
	<b>Min</b>	<b>Max</b>	<b>Recommended</b>																								
<b>Wet Film Per Coat (microns)</b>	893	1451	1116																								
<b>Dry Film Per Coat (microns)</b>	400	650	500																								
<b>Recoat Time (min)</b>	4 Hours	Indefinite																									
<b>Theoretical Spread Rate (m<sup>2</sup>/L)</b>	1.1	0.7	0.9																								
<b>Dulux Colour Base</b>	EXTRA BRIGHT																										

Application Guide	
<b>Surface Preparation</b>	<ul style="list-style-type: none"> <li>All surfaces must be cured, clean, sound and free of all contaminants such as forms oils, release agents &amp; mortar splashes. Surface imperfections misalignments &amp; protrusions must be levelled, patched &amp; completely flush to surrounding surfaces. Metal, tie wire etc on surface must be removed or treated against corrosion. Prime substrate with DULUX AcraTex AcraPrime WB. Ensure that it is cured completely and covers the substrate evenly.</li> </ul>
<b>Application Procedure And Equipment</b>	<ul style="list-style-type: none"> <li>brush and long nap roller / lambswool mitt</li> <li>Refer to the DULUX AcraTex Application Manual for detailed instructions. Product should be tinted and thoroughly mixed before use. Application is by brush or nap roller in a patina motion ( criss cross). A single coat is required (minimum DFT of 400 micrometres) a second coat may be applied to avoid "holidays" in the coating. This texture is applied in a an uneven appearance to simulate that of " Bagged Finished Render" over flush jointed brick or blockwork via a brush or lambswool mitt. A site sample of no less than 1 sqm should be applied and be approved by the client prior to application.</li> <li>Site sample should be undertaken before the project commences.</li> </ul>

Health And Safety			
<b>MSDS Number</b>	DLX003091		
<b>MSDS Link</b>	<a href="https://go.lupinsys.com/duluxgroup/harms/public/materials/35f7010af1be44e6a8669efe41d3f2dc-published/individual">https://go.lupinsys.com/duluxgroup/harms/public/materials/35f7010af1be44e6a8669efe41d3f2dc-published/individual</a>		
<b>Health Effects</b>	For detailed information refer to the product label and the current Material Safety data Sheet available through Dulux Sales and Customer Service Offices 13 25 25 AUS. For emergencies, please call Australia 1800 220 770 or New Zealand 0800 220 770.  Ensure adequate ventilation. Take suitable safety precautions while preparing your surface or sanding a previously coated surface, including wearing an appropriate respiratory mask  Health Effects: Splashes to the eye may cause eye irritation. Personal Protective Equipment: Wear eye protection.	<b>Flammability</b>	Non Flammable
<b>Storage</b>	Store out of direct Sunlight in a cool area		
<b>In the case of emergency, please call 1800 033 111</b>			

Transport And Storage			
<b>Pack A</b>	194-85950	<b>Shipment Name</b>	Not dangerous goods.
<b>Size</b>	15 litre	<b>Weight</b>	24 kg
<b>Flash Point</b>	N/A	<b>UN Number</b>	N/A
<b>Dangerous Goods Class</b>	N/A	<b>Package Group</b>	N/A



**Disclaimer**

Dulux, Selleys and Other marks followed by ® are registered trademarks. Marks followed by the symbol of ™ are trademarks.

The data provided within the Duspec system is correct at the time of publication, however it is the responsibility of those using this information to check that it is current prior to specifying or using any of these coating/product systems.  
 DISCLAIMER: Any advice, recommendation, information, assistance or service provided by any of the divisions of DuluxGroup (Australia) Pty Ltd or its related entities (collectively, DuluxGroup) in relation to goods manufactured by it or their use and application is given in good faith and is believed by DuluxGroup to be appropriate and reliable. However, any advice, recommendation, information, assistance or service provided by DuluxGroup is provided without liability or responsibility PROVIDED THAT the foregoing shall not exclude, limit, restrict or modify the right entitlements and remedies conferred upon any person or the liabilities imposed upon DuluxGroup by any condition or warranty implied by Commonwealth, State or Territory Act or ordinance void or prohibiting such exclusion limitation or modification. Coating/product systems can be expected to perform as indicated on the Duspec Spec Sheet so long as applications and application procedures of the individual products are followed as recommended on the appropriate Product data Sheet. "DuluxGroup" "Dulux" "Selleys" "Berger" "Berger Gold Label" "Hadrian" "Walpamur" "Levene" "AcraTex" and Other marks followed by ® are registered trademarks of DuluxGroup (Australia) Pty Ltd ABN 67 000 049 427. Marks followed by the symbol ™ are trademarks.

Please note that this document is only valid for 60 days from the date of issue.

DuluxGroup (Australia) Pty Ltd 1956 Dandenong Road, Clayton, Victoria 3168 AU ABN 67 000 049 427